



Spicers Paper

Kantac Mirrorkote C58

Mirrorkote is a high gloss white cast coated paper. Its mirror finish provides ideal contrast and brilliance for a multitude of label uses. Particularly suited to high quality, multi-coloured labels, with exceptional mechanical and humidity resistance. Typical end use applications include:

- Prestige point of sale labels for household goods and cosmetic packaging.
- Excellent eye-catching wine labels, so important for the image of the wine inside the bottle.
- High class beverage and food stuff labelling where a lasting crisp finish lends itself to the image of the product.

Mirrorkote accepts most common forms of printing processes including rotary and flat bed letterpress, flexography and offset. Mirrorkote also die-cuts and hot stamps excellently.

Face Material Properties

Grammage	85 +/- 5 g/m ²	ISO 536
Caliper	94 +/- 5 microns	ISO 534
Tensile Strength MD	Min 5.0kg/15mm	
Tensile Strength CD	Min 3.5kg/15mm	
Smoothness Bekk 5/10ml	190+/- 50	

Adhesive

C58

Chill Permanent

A water bourn acrylic emulsion with excellent initial and final tack. A superior cold temperature adhesive with superior adhesive force where condensation is present. Adheres easily with minimal pressure – excellent initial tack and final tack.

C58 is suitable for application to difficult surfaces such as recycled cartons and narrow diameters etc.

Composition	Water Bourne Acrylic
Initial tack	1100g/25mm
Adhesion	1800g/25mm
Ball Tack	11mm
Minimum Application Temperature	0 °C to +40 °C
Service Temperature	-30 to +60 °C
Food contact	direct food contact for dry non-fatty foods

Backing

SG6W

This backing paper is a 64gsm white glassine, convenient for the high speed printing and stripping of both rotary and flat bed letterpress labels. Its thickness, stability and hardness ensures excellent performance with label printing machines and automatic applicators.

Grammage	64gsm	
Calliper	57 microns	ISO 534
Tensile Strength MD	Min 5.9kg/15mm	
Tensile Strength CD	Min 3.4kg/15mm	

Laminate

Laminate Shelf Life	48 months stored at 20°C/50% RH
Typical Laminate Calliper	169 microns

NOTE:

All statements, technical information and recommendation are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed, and the following is made in lieu of all warranties of merchantability and fitness for the purpose: Sellers and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Before using, user shall determine the suitability of the product for its intended use, and user assumes all risk and liability whatsoever in connection therewith.